

LIST OF CLAIMS

1. - 12. (Canceled)

13. (Previously Presented) A process for producing a cured molded article consisting essentially of the step of:

 primarily curing a fluororubber composition comprising
 100 parts by weight of a fluororubber which is curable with
an organic peroxide,

 0.1 to 10 parts by weight of a polyfunctional unsaturated
compound, and

 0.3 to 1.2 parts by weight of an organic peroxide selected
from the group consisting of dicumyl peroxide, tert.-butylcumyl
peroxide and di-tert.-butyl peroxide, at a temperature of 150 to
190°C for 0.1 to 1 hour,

 wherein the total amount of acetone and tert.-butanol
contained in the decomposed products of one mole of said organic
peroxide, which are generated at a curing temperature, is 2
moles or less.

14. (Previously Presented) A process according to claim 13,
wherein said cured molded article is an O-ring.

15. (New) The process according to claim 13, wherein the amount
of said organic peroxide is from 0.4 to 1.0 parts by weight.